

PRODUCT CHARACTERISTICS

Provides a tough impermeable barrier suitable for steel and concrete surfaces.
Excellent resistance to severe chemical, corrosive and abrasive environments.
Especially suitable for structural steel and marine environments.
Low maintenance and ease of reparability with good UV resistance.
Approved for food contact.

PRODUCT DESCRIPTION

Two pack isophthalic polyester resin reinforced with screened glassflake.
Gives a nearly smooth finish that can be made to any colour.

PRODUCT INFORMATION

Colour:	Standard off white (other colours available on request).
Volume solids:	100%
Mix ratio:	Hardener (HA 200) 1% - 3% volume by weight (depending on temperature and other environmental factors).
Cure:	Catalyst induced cross-linking polymerisation.
Typical thickness range:	350 - 1000 microns per coat.
Theoretical coverage:	1.5m ² /kg @ 500 microns. (Allow for application losses, surface irregularities, etc).
Temperature resistance:	85°C

APPLICATION DATA

Method:	Airless spray, roller, brush or trowel.
Thinner:	No thinning agents to be added.
Cleaner:	S11
Recoating interval:	Minimum: 30 mins - 2hrs (touch dry). Maximum: unlimited.
Pot life:	30 - 80 minutes @ 23°C
Curing time:	24 hrs @ 15°C (depending on temperature and other environmental conditions).

APPLICATION

Constituents:	Polyester resin and hardener.
Airless spray:	Airless spray pump (minimum 45:1) with a fluid twist tip: RE 264 (27 - 33 thou. Ideal 31 thou.) RE 232 (33 - 42 thou. Ideal 36 thou.)
Brush, roller or trowel:	For inaccessible or awkward areas, or when spray application is not required or feasible. For application of RE 208 (largest screened glassflake polyester coating). To obtain correct orientation of screened glassflake particles, use a styrene-dipped roller. Please refer to application instruction for full details.

LIMITATIONS

Pot life: Vigilant care and attention to pot life is required during application. If gelling has started, do not apply.

Airless spraying: Suitable only for coatings reinforced with 0.4mm (RE 264) and 0.8mm (RE 232) screened glassflake particles.

ENVIRONMENTAL CONDITIONS

Blasting or coating application should **NOT** be carried out when :-

- Relative humidity is above 85%
- Air temperature < 5°C
- Steel temperature < 3°C above dew point of surrounding air.

SAFETY PRECAUTIONS

It is the policy of CHEMCO INTERNATIONAL (C.I.) to ensure that its products are handled and applied by professionally approved and skilled applicators.

Application shall be carried out in accordance with instructions contained in this data sheet and referenced to C.I. TECHNICAL SPECIFICATION MANUAL.

CHEMCO INTERNATIONAL management are intent on ensuring all work is carried out in accordance with company HEALTH & SAFETY procedures and all materials are handled with due care to COSHH regulations and instructions.

STORAGE

Store in cool, dry conditions (below 20°C) keep away from direct heat source and sunlight.

When not using the material always replace the lid on the container.

SHELF LIFE

At least 12 months when stored in sealed containers at temperatures of 20°C or below.

At temperatures above, refer to manufacturer for advice.

DISCLAIMER The information contained herein is to the best of our knowledge accurate and current and is given in good faith without warranty. Users are deemed to have satisfied themselves independently as to the suitability of our products for their particular purpose. In no event shall Chemco International be liable for consequent or incidental damages.



East Shawhead Industrial Estate
Coatbridge ML5 4XD Scotland
Tel: +44 (0) 1236 606060
Fax: +44 (0) 1236 606070
email: sales@chemcoint.com
web site: www.chemcoint.com