

PRODUCT CHARACTERISTICS

Epoxy coating formulated with ceramic technology to withstand hardwearing and abrasive stresses. Forms an impermeable barrier, suitable for repair work on all types of fluid flow equipment and for tank linings.

Imparts excellent chemical and thermal resistance properties with a low friction finish to offer Improved efficiency.

Specifically formulated to resist high temperature, aggressive chemical and fluid flow environments: -

- Pumps
- Pipes
- Heat Exchangers
- Tube Sheets
- Castings
- Impellers/Propellers
- Tanks
- Diffusers
- Cracked casings
- Fan Blades
- Valves
- Bow Thrusters

Deep pitting and voids can be filled quickly with RW 532/RW 508

RW 532/RW 508 is fully machineable and has excellent adhesion with RU 500

User-friendly and easy to apply.

Effective one-coat system which can be easily over-coated if required.

PRODUCT DESCRIPTION

Two pack epoxy novolac, incorporating **Cerpofix™** high performance technology.

PRODUCT INFORMATION

Colour:	Standard orange.	
Pack sizes:	Standard 1, 2 and 5kgs	
Solids content:	100%	
Mix ratio:	Mix part A (resin RU 500) and part B (hardener HU 500) in proportionate weights as supplied.	
Mix density:	1.28g/ml	
Cure:	10°C	20°C
Pot life:	80 mins	45 mins
Touch dry:	8 hrs	5 hrs
Hard dry:	24 hrs	12 hrs
Full cure:	7 days	3 days
Typical thickness range:	200 - 400 microns per coat.	
Theoretical coverage:	3.1m ² /kg @ 250 microns.	
	1.95m ² /kg @ 400 microns.	
	(Allow for application losses, surface irregularities, etc).	
Temperature resistance:	Immersed:	125°C
	Dry:	200°C
	Maximum:	220°C

APPLICATION DATA

Method:	Brush or roller.
Thinner:	No thinning agents required.
Cleaner:	S11 or S11A
Recoating interval:	Minimum: 4 - 8 hrs (touch dry) @ 20°C
	Maximum: 24 hrs @ 20°C

SURFACE PREPERATION

Metallic surfaces:

Remove all loose contamination by wire brushing. Remove any dirt, oil, grease, etc. using a suitable cleaner/degreaser that does not leave a residue. A suitable angular metallic or non-metallic abrasive should be chosen to give a minimum profile of 50 microns. Abrasive blast the metal surface to ISO 8501-1 SA 2½. After blasting, the surface should be coated before any oxidation takes place.

Metallic surfaces which have been immersed for any period in salt solution, e.g. seawater, should go through a blast/wash/blast cycle (wash with clean potable water) or baked to remove all salt residues. The process should be repeated until all traces of salts have been removed.

LIMITATIONS

Pot life:

Vigilant care and attention to pot life is required during application. If gelling has started, do not apply.

SAFETY PRECAUTIONS

It is the policy of CHEMCO INTERNATIONAL (C.I.) to ensure that its products are handled and applied by professionally approved and skilled applicators. Application shall be carried out in accordance with instructions contained in this data sheet and referenced to C.I. TECHNICAL SPECIFICATION MANUAL. CHEMCO INTERNATIONAL management are intent on ensuring all work is carried out in accordance with company HEALTH & SAFETY procedures and all materials are handled with due care to COSHH regulations and instructions.

STORAGE

Store in cool, dry conditions (between 2 - 20°C). Keep away from direct heat source and sunlight. When not using the material, always replace the lid on the container.

SHELF LIFE

At least 12 months when stored in sealed containers at temperatures of 20°C or below. At temperatures above, refer to manufacturer for advice.

DISCLAIMER The information contained herein is to the best of our knowledge accurate and current and is given in good faith without warranty. Users are deemed to have satisfied themselves independently as to the suitability of our products for their particular purpose. In no event shall Chemco International be liable for consequent or incidental damages.



East Shawhead Industrial Estate
Coatbridge ML5 4XD Scotland
Tel: +44 (0) 1236 606060
Fax: +44 (0) 1236 606070
Email: sales@chemcoint.com
Web Site: www.chemcoint.com