

APPLICATION (cont'd)

Surface preparation for aged and new galvanised substrate.
(Network Rail Specification X099)

Aged/weathered galvanised:	Degrease with solvent, abrade with Scotchbrite pad followed by a final solvent wipe.
New galvanise:	Degrease with solvent, abrade with Scotchbrite pad, solvent rinse and treat with T-wash.

Surface preparation for existing weathered paintwork.
(Network Rail Protective Treatment XM9)

Wash and degrease:	Abrade of the existing sound paintwork. Spot blast-clean localised corrosion to surface standard SA 2½ (BS7079: Part A1). Lightly abrade sound alkyd paintwork.
--------------------	---

LIMITATIONS

Pot life:	Vigilant care and attention to pot life is required during application. If gelling has started, do not apply.
-----------	---

SAFETY PRECAUTIONS

It is the policy of CHEMCO INTERNATIONAL (C.I.) to ensure that its products are handled and applied by professionally approved and skilled applicators. Application shall be carried out in accordance with instructions contained in this data sheet and referenced to C.I. TECHNICAL SPECIFICATION MANUAL. CHEMCO INTERNATIONAL management are intent on ensuring all work is carried out in accordance with company HEALTH & SAFETY procedures and all materials are handled with due care to COSHH regulations and instructions.

STORAGE

Store in cool, dry conditions (below 20°C). Keep away from direct heat source and sunlight. When not using the material, always replace the lid on the container.

SHELF LIFE

At least 12 months when stored in sealed containers at temperatures of 20°C or below. At temperatures above, refer to manufacturer for advice.

DISCLAIMER The information contained herein is to the best of our knowledge accurate and current and is given in good faith without warranty. Users are deemed to have satisfied themselves independently as to the suitability of our products for their particular purpose. In no event shall Chemco International be liable for consequent or incidental damages.



East Shawhead Industrial Estate
Coatbridge ML5 4LY Scotland
Tel: +44 (0) 1236 606060
Fax: +44 (0) 1236 606070
Email: sales@chemcoint.com
Web Site: www.chemcoint.com