

PRODUCT CHARACTERISTICS

Innovative water-base system offering outstanding protection and environmentally safe solutions for the repair and maintenance to concrete and masonry surfaces at a cost-competitive price. Easy to apply, intrinsically safe and environmentally friendly with no harmful odours. The product is fast setting and dries to form an extremely tough finish that will not crack. The system may be supplied in two formats: -

- **RL 800CRS-LV: Self-levelling underlay** recommended for resurfacing unsealed, flaking, porous, aged, damaged and/or eroded concrete. Ideal for filling in large cavities, cracks and heavy pitting in concrete and masonry. Thickness limitation: 10mm
- **RL 800CRS-HV: Heavy-duty/water-base mortar** recommended for the complete re-lining of old tanks and bunded area(s) etc. Dries to form a smooth surface and is ideal for patch repair. Thickness limitation: 20mm

PRODUCT DESCRIPTION

Water-base modified polymer repair system.

PRODUCT INFORMATION

Colour:	Standard grey (others colours available on request).	
Pack sizes:	5 and 25kgs	
Solids content:	RL 800CRS-LV	RL800CRS-HV
Density:	88%	90%
Temperature resistance:	1.9g/cm ³	1.93g/cm ³ @ 20°C
	Max 80°C	Max 80°C

APPLICATION DATA

Method:	RL 800CRS-LV:	Spiked roller and/or squeegee.
	RL 800CRS-HV:	Trowel and/or spatula.
Thinner:	No thinning agents to be added.	
Cleaner:	Water.	
Pot life:	RL 800CRS-LV	RL 800CRS-HV
	(depending on thickness @ 15°C)	(depending on thickness @ 15°C)
	1 - 2 hrs	unlimited.
Touch dry:	5 - 10 hrs	3 - 4 hrs
	(depending on thickness @ 5 - 10mm and temperature of 25°C)	
Drying time:	24 - 72 hrs	24 - 72 hrs
	(depending on thickness @ 25°C)	

APPLICATION

Mixing:

RL 800CRS-LV:-

Mix components (part B aggregate) to part A (resin RL 800CRS) at ambient temperatures thoroughly to achieve an even consistency.

Resin and hardener are supplied in pre-weighed quantities in a range of pack sizes suitable for the particular application.

It is important therefore, that applicators use all of the materials as supplied when mixing to achieve full cure.

Part mixing is not recommended.

RL 800CRS-HV:-

The product is supplied as a single pack system, therefore mixing is not required.

ENVIRONMENTAL CONDITIONS

Blasting or application should **NOT** be carried out when :-

Relative humidity is > 85%

Air temperature < 5°C

Substrate temperature < 3°C above dew point of surrounding air.

SAFETY PRECAUTIONS

It is the policy of CHEMCO INTERNATIONAL (C.I.) to ensure that its products are handled and applied by professionally approved and skilled applicators.

Application shall be carried out in accordance with instructions contained in this data sheet and referenced to C.I. TECHNICAL SPECIFICATION MANUAL.

CHEMCO INTERNATIONAL management are intent on ensuring all work is carried out in accordance with company HEALTH & SAFETY procedures and all materials are handled with due care to COSHH regulations and instructions.

STORAGE

Store in cool, dry conditions (below 20°C). Keep away from direct heat source and sunlight. When not using the material, always replace the lid on the container.

SHELF LIFE

At least 12 months when stored in sealed containers at temperatures of 20°C or below.

At temperatures above, refer to manufacturer for advice.

DISCLAIMER The information contained herein is to the best of our knowledge accurate and current and is given in good faith without warranty. Users are deemed to have satisfied themselves independently as to the suitability of our products for their particular purpose. In no event shall Chemco International be liable for consequent or incidental damages.



East Shawhead Industrial Estate
Coatbridge ML5 4XD Scotland
Tel: +44 (0) 1236 606060
Fax: +44 (0) 1236 606070
Email: sales@chemcoint.com
Web Site: www.chemcoint.com