

PRODUCT CHARACTERISTICS

Multi-purpose, low odour epoxy coating, which is suitable for application in environments where solvents would be hazardous or have a detrimental affect upon the operating process or products.

The coating is very adaptable and user-friendly, long pot life and short drying time provides optimum benefits of productivity and reduced downtime to both client and contractor.

Safe, easy to use coating, which does not yellow; may be formulated for walls or ceilings and is ideal for hygienic environments.

The coating can be applied to concrete, metal, wood, stone and tiled surfaces.

System can be formulated for specialist application, offering anti-static, non-skid or anti-slip finish.

Recommended for hospitals, public utilities, food processing industry (e.g. abattoirs) and clean-rooms (particularly electronics industry).

PRODUCT DESCRIPTION

Two pack water-based epoxy coating.

PRODUCT INFORMATION

Colour:	Standard white (other colours available on request).
Volume solids:	60% ± 2%
Mix ratio:	Mix part A (resin RX 800) and part B (hardener HX 800) in proportionate weights as supplied.
Typical thickness range:	60 microns dft from 100 microns wft.
Theoretical coverage:	12m ² /kg approx. (Dependent on surface roughness, porosity and complexity of structure).

APPLICATION DATA

Method:	Brush, lambswool roller (preferred method for floor application) and spray.		
Thinner:	Clean water.		
Cleaner:	Clean water.		
Pot life:	2 - 3 hrs @ 20°C		
Drying time:	@ 20°C		
	Touch	Hard	Overcoating
	Dry	Dry	Interval
	30 - 40 mins	4 - 8 hrs	8 - 24 hrs

SURFACE PREPARATION

When preparing concrete substrates for application, it is very important to ensure that surface laitance has been completely removed. Method of preparation can either be by abrasive blasting (blastrack), scarifying or by acid etching. For further information refer to application instruction or consult Chemco sales and technical department.

LIMITATIONS

Pot life:	Apply the mixed components within the given pot life. No visible physical change takes place when pot life has expired. It is essential that applicator monitors pot life time and has a copy of the general information data sheet to hand when coating.
Mixing:	Part A should be added to container B and mixed. Mix thoroughly using a mechanical mixer to achieve an even consistency.

ENVIRONMENTAL CONDITIONS

Do **NOT** apply coating at temperatures below 10°C. Ideal conditions when coating may be applied are: -

Relative humidity < 70%
Efficient air supply or good ventilation is critical.

SAFETY PRECAUTIONS

It is the policy of CHEMCO INTERNATIONAL (C.I.) to ensure that its products are handled and applied by professionally approved and skilled applicators.

Application shall be carried out in accordance with instructions contained in this data sheet and referenced to C.I. TECHNICAL SPECIFICATION MANUAL.

CHEMCO INTERNATIONAL management are intent on ensuring all work is carried out in accordance with company HEALTH & SAFETY procedures and all materials are handled with due care to COSHH regulations and instructions.

STORAGE

Store in cool, dry conditions (between 2 and 40°C). Keep away from direct heat source and sunlight. When not using the material always replace the lid on the container.

SHELF LIFE

At least 12 months when stored in sealed containers at temperatures of 20°C or below.
At temperatures above, refer to manufacturer for advice.

DISCLAIMER The information contained herein is to the best of our knowledge accurate and current and is given in good faith without warranty. Users are deemed to have satisfied themselves independently as to the suitability of our products for their particular purpose. In no event shall Chemco International be liable for consequent or incidental damages.



East Shawhead Industrial Estate
Coatbridge ML5 4XD Scotland
Tel: +44 (0) 1236 606060
Fax: +44 (0) 1236 606070
Email: sales@chemcoint.com
Web Site: www.chemcoint.com